

WOOD FILLER TUBE

Description

Ready mixed wood filler

Intended use

- Filling holes & cracks on doors, window frames, skirting boards & floor boards



Product advantages

- + Flexible
- + Fibre glass reinforced
- + Quick drying
- + Easy to apply & sand
- + Suitable for use on most types of wood



ENVIRONMENTAL DATA

INDOOR AIR EMISSIONS

Information on the level of emissions of volatile substances into indoor air presenting a risk of toxicity by inhalation, on a class scale from A+ (very low emissions) to C (high emissions)



COMPOSITION

70% OF RAW MATERIALS
% OF NATURAL ORIGIN

Calcium carbonate, water

V.O.C CONTENT

VOC Directive 2004/42/EC: Cat A/a EU limit value: 30 g/L
This product contains a maximum 30 g/L PAE

PACKAGING

No recycled / non-recyclable

MANUFACTURING

This product is manufactured in our factory whose environmental management system is certified by Afnor



Beissier is committed to the sustainable development of its activities and has integrated CSR into its strategy our company has achieved an exemplary level on the "Engagé RSE label" assessment benchmark



WOOD FILLER TUBE

USE

DILUTION

Ready mixed

APPLICATION

▪ Conditions

Do not apply at temperatures of below + 5°C or above + 35°C, or at a relative humidity of above 80% H.R.

▪ Equipment

Filling knife, blade

▪ Operational mode

Massage tube before application. Work the filler into the repair and leave slightly proud for sanding. For deep repairs fill in two or more layers. Once dry sand and then stain, varnish or paint.

▪ Equipment cleaning

With water before completely dry. Do not throw away into drains, dispose of this material and its container to an approved disposal contractor or taken to municipal collection point. Do not dispose into the environment.

RECOMMENDATIONS

Exterior use : the filler must be over coated with a weather proof stain, varnish or paint. Do not apply on damp wood.

AVERAGE CONSUMPTION

1,4 kg/m² per mm thickness
(Depending on application thickness)

SUBSTRATES

Most types of wood, chipboard, plywood. DO NOT APPLY ON DAMP WOOD.

Substrates must be clean, dry and free from dust, grease & wax.

Metallic parts must be primed, according to the local standards.

OVERCOAT

Primer, wood stains, varnish or paint

WORKING TIME AT 20°C

Unlimited

WAITING TIME BEFORE OVERCOATING

1 – 4 hours

TECHNICAL DATA

COMPONENTS

Polymer base aqueous phase coat mix, mineral fillers, additives.

DENSITY

1,4 ± 0,1

pH

8 ± 1

COLOUR

White, natural, medium, dark

CLASSIFICATION

NF T 36-005 - Family IV, class 4b

NORM

NF EN 16566

HEALTH AND SAFETY



Use in a well-ventilated place. Avoid direct contact with skin and eyes. In case of prolonged contact, it is recommended to wear suitable gloves. Application by projection, wearing glasses and a mask is recommended. Safety data sheet available on www.beissier.eu or www.quickfds.com

PACK SIZES

125 ml tube

STORAGE

12 months from date of manufacture, in unopened original packaging, protected from frost, heat (max. +30°C), sun and moisture. Close well after use. Store in original packaging.

This data sheet supersedes and replaces any prior sheet relating to the same product. Date of issue : **July 2025**

The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility, prior to use, to check with us that updated edition of this sheet has not been issued.



France - Quartier de la Gare, 77760 La Chapelle la Reine
Becket House - 1 Lambeth Palace Road - London - SE1 7EU

020 7092 6696 • www.beissier.eu

FOLLOW US ON



FIND MORE ABOUT US THROUGH OUR NETWORK

